30

TPC)	TYPICAL DATA SHEET*	ISSUE DATE	Mar-16
	GRADE	<u>WWW.TPCO.IR</u>	
	LL0220AA	IRAN/TABRIZ/TABRIZ PETROCHEMICAL COMPANY/P.O.BOX:51745-354/TEL:+984134282612	

LL0220AA is linear low density polyethylene copolymer containing butene-1(C4) as comonomer. It is suitable for blending with conventional LDPE for cast film applications.

Film made from pure LL0220AA has the following advantages over LDPE:

 $good\ balance\ of\ mechanical\ properties, good\ optical\ properties. This\ grade\ has\ food\ contact\ approval$

Applications:

light and medium duty films, stretch film

PROPERTY	UNIT	TEST METHOD	TYPICAL VALUE
MELT FLOW INDEX(2.16KG)	g/10min	ASTM D-1238	2.4
DENSITY	gr/cm3	ASTM D-1505	0.921
VICAT SOFTENING POINT	°C	ASTM D-1525	100
FILM**			
DART DROP IMPACT METH	OD A GR	ASTM D-1709	90
TENSILE STRESS AT YEILD MD/	TD MPA	ASTM D-882	10/11
TENSILE STRESS AT BREAK MD/	TD MPA	ASTM D-882	30/25
ELONGATION AT BREAK MD/		ASTM D-882	1000/1100
HAZE -	%	ASTM D-1003	1

^{*}All above mentioned data are typical values and not to be construed as real specifications. Users should confirm results by their own tests. For more information about guaranteed items, please refer to S.S.S. (Standard Sales Specifications)

ASTM D-2457

%°

Grade Suffix(Additives Indication):

GLOSS(45°)

AA:GENERAL ANTIOXIDANT

^{**38} μ m film,2.5:1 blow up ratio,225°c melt temperature , MD: Machine Direction,TD:Transverse Direction