

Microthene® RL

MR SP010

Melt Bonding Polyethylene Powder (Black) Rotolining and Powder Coating Grade Melt Index 5.5 Density 0.939

Applications

MICROTHENE MR SP010 is a modified thermoplastic polyethylene-based rotolining and powder coating resin, available as a 35-mesh powder containing carbon black. MR SP010 offers exceptional stress crack resistance and excellent adhesion to metals and selected polymers. Typical applications include linings and coatings for pipes, drums, hollow vessels and irregularly shaped parts. MR SP010 provides resistance to a wide range of chemicals and is designed for applications requiring corrosion resistance, insulation or abrasion and impact resistance.

Processing Techniques

Application methods include rotational lining, co-rotational lining, powder spray and fluidized bed coating. A melt temperature of 450° to 550°F is recommended for processing MR SP010. However, optimum bonding is a function of temperature, time and method of application. More specific suggestions can be made only when the lining/coating substrate, processing equipment, conditions and end uses are known. For further information, please contact your Equistar sales representative.

Physical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	5.5	g/10 min	D 1238
Density	0.939	g/cc	D 1505
Tensile Strength @ Yield, 2"/min *	1,760 (12.1)	psi (MPa)	D 638
Elongation, Ultimate, 2"/min *	>900	%	D 638
Heat Distortion Temperature @66 psi	122 (50)	°F (°C)	D 648
@264 psi	97 (36)	°F (°C)	D 648
Environmental Stress Crack Resistance, F ₅₀			
100% Igepal®	>1,000	hrs	D 1693
10% Igepal®	>1,000	hrs	D 1693
Flexural Modulus, 1% Secant	71,000 (490)	psi (MPa)	D 790
Low Temperature Impact			
1/8" specimen	50	ft-lbs	ARM STD
1/4" specimen	>150	ft-lbs	-40 °F Impact

* Type IV specimen

®Igepal is a registered trademark of the Rhone-Poulenc Co., Inc.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at (800) 700-0946.

® Equistar and Microthene are registered trademarks of Equistar Chemicals, LP.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999



EQUISTAR